

RYSZARD SPRYCHA ET AL.
USSN 09/982,496
REPLY TO THE OFFICE ACTION DATED FEBRUARY 20, 2004
AMENDMENT OF JANUARY 21, 2005

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Previously Presented) A non-aqueous lamination ink formulation or dispersion comprising: (a) a resin; (b) a non-fluorescent pigment; (c) an organic solvent; and (d) a viscosity stabilizing, resolubility promoting, water soluble compound selected from the group consisting of base, aminoalcohol, acid and aminoacid.
2. (Original) The ink formulation or dispersion of claim 1, wherein the resin is a polyamide resin.
3. (Previously Presented) The ink formulation or dispersion of claim 1, wherein the non-fluorescent pigment is selected from the group consisting of monoazo yellow, monoarylide yellow, diarylide yellow, naphthol red, rubine red, lithol rubine, phthalocyanine blue and carbon black.
4. (Original) The ink formulation or dispersion of claim 1, wherein the organic solvent is selected from the group consisting of ethanol, n-propanol, iso-propanol, butanol and propyl acetate.
5. (Original) The ink formulation or dispersion of claim 1, wherein the amount of the water soluble compound is about 0.01 to 5.0% by weight of the total weight of the formulation or dispersion.

RYSZARD SPRYCHA ET AL.

USSN 09/982,496

REPLY TO THE OFFICE ACTION DATED FEBRUARY 20, 2004

AMENDMENT OF JANUARY 21, 2005

6. (Original) The ink formulation or dispersion of claim 1, wherein the amount of the water soluble compound is about 0.1 to 1.0% by weight of the total weight of the formulation or dispersion.

7. (Previously Presented) The ink formulation or dispersion of claim 1, wherein the base is an inorganic or organic base.

8. (Original) The ink formulation or dispersion of claim 7, wherein the inorganic base is selected from the group consisting of sodium hydroxide, potassium hydroxide and ammonium hydroxide.

9. (Previously Presented) The ink formulation or dispersion of claim 7, wherein the organic base is an amine.

10. (Currently Amended) The ink formulation or dispersion of claim 9, wherein the amine is selected from the group consisting of monoethanolamine, triethanolamine, dimethylethanolamine and diethylenetriamine.

11. (Original) The ink formulation or dispersion of claim 1, wherein the aminoalcohol is selected from the group consisting of aminopropanol, aminoethylpropanediol, aminobutanol, diethylaminoethanol and dimethylaminopropanol.

12. (Original) The ink formulation or dispersion of claim 1, wherein the acid is organic or inorganic acid.

13. (Original) The ink formulation or dispersion of claim 12, wherein the inorganic acid is selected from the group consisting of hydrochloric acid, nitric acid and sulfuric

RYSZARD SPRYCHA ET AL.
USSN 09/982,496
REPLY TO THE OFFICE ACTION DATED FEBRUARY 20, 2004
AMENDMENT OF JANUARY 21, 2005

acid.

14. (Original) The ink formulation or dispersion of claim 12, wherein the organic acid is selected from the group consisting of acetic acid, citric acid, and paraaminobenzoic acid.

15. (Currently Amended) A method of increasing the stability and resolubility of a non-aqueous inks formulations or dispersions containing (a) a resin; (b) a pigment; and (c) an organic solvent comprising adding to said formulation or dispersion a water-soluble compound selected from the group consisting of base, aminoalcohol, acid and aminoacid.

16. (Original) The method of claim 15, wherein the resin is a polyamide resin.

17. (Original) The method of claim 15, wherein the pigment is selected from the group consisting of monoazo yellow, monoarylide yellow, diarylide yellow, naphtol red, rubine red, lithol rubine, phthalocyanine blue and carbon black.

18. (Original) The method of claim 15, wherein the organic solvent is selected from the group consisting of n-propanol, iso-propanol, butanol, ethanol and propyl acetate.

19. (Currently Amended) The method of claim 15, wherein the amount of the water soluble compound is about 0.01 to 5.0% by weight of the total weight of the formulation or dispersion.

20. (Original) The method of claim 15, wherein the amount of the water soluble compound is about 0.1 to 1.0% by weight of the total weight of the formulation or dispersion.

21. (Original) The method of claim 15, wherein the base is inorganic or organic base.

RYSZARD SPRYCHA ET AL.

USSN 09/982,496

REPLY TO THE OFFICE ACTION DATED FEBRUARY 20, 2004

AMENDMENT OF JANUARY 21, 2005

22. (Original) The method of claim 21, wherein the inorganic base is selected from the group consisting of sodium hydroxide, potassium hydroxide and ammonium hydroxide.
23. (Original) The method of claim 21, wherein the organic base is amine or aminoalcohol.
24. (Currently Amended) The method of claim 23, wherein the amine is selected from the group consisting of monoethanolamine, triethanolamine, dimethylethanolamine and diethylenetriamine.
25. (Original) The method of claim 15, wherein the aminoalcohol is selected from the group consisting of aminopropanol, aminoethylpropanediol, aminobutanol, diethylaminoethanol and dimethylaminopropanol.
26. (Original) The method of claim 15, wherein the acid is organic or inorganic acid.
27. (Original) The method of claim 26, wherein the inorganic acid is selected from the group consisting of hydrochloric acid, nitric acid and sulfuric acid.
28. (Original) The method of claim 26, wherein the organic acid is selected from the group consisting of acetic acid, citric acid and paraaminobenzoic acid.
29. (Currently Amended) An improved non-aqueous lamination ink formulation or dispersion comprising: (a) a resin; (b) a non-fluorescent pigment; (c) an organic solvent; wherein the improvement is (d) a viscosity stabilizing, resolubility promoting water soluble compound selected from the group consisting of base, aminoalcohol, acid and aminoacid.